



**SETSCO SERVICES PTE LTD**

18 Teban Gardens Crescent  
Singapore 608925  
Tel : (65) 6566 7777  
Fax: (65) 6566 7718  
Website: www.setsco.com  
Business Reg. No. 196900269D

(This Report is issued subject to the terms & conditions set out below)

Our Reference: BP-266

26 July 2006

**REPORT  
ON  
TESTS, EXPERIMENTS AND SIMULATIONS ON 'INSULTEC' PAINT**

**PREPARED FOR:**

**MULTI-SINDO (SINGAPORE) PE LTD**  
1 GOLDHILL PLAZA #02-19  
SINGAPORE 308899  
**ATTN: MR. GUY DE SOUZA**

**PREPARED BY:**

**NICOLAS MOOSSA**  
**ASSISTANT MANAGER**

**WONG CHUNG WAN**  
**DIVISION DIRECTOR**  
**CONSTRUCTION TECHNOLOGY DIVISION**

*Building Consultancy Department  
Materials Consultancy, Building Audit  
Forensic Engineering, Risk Assessment  
Architectural Engineering*

**Terms & Conditions**

- (1) The Report is prepared for the sole use of the Client and is prepared based upon the Item submitted, the services required by the Client and the conditions under which the Services are performed by SETSCO. The Report is not intended to be representative of similar or equivalent Services on similar or equivalent Items. The report does not constitute an endorsement by SETSCO of the Item.
- (2) SETSCO agrees to use reasonable diligence in the performance of the Services but no warranties are given and none may be implied directly or indirectly relating to the Services, the Report or the facilities of SETSCO.
- (3) The Report may not be used in any publicity material without the written consent of SETSCO.
- (4) The Report may not be reproduced in part or in full unless approval in writing has been given by SETSCO.
- (5) SETSCO shall under no circumstances be liable to the Client or its agents, servants or representatives, in contract, tort (including negligence or breach of statutory duty) or otherwise for any direct or indirect loss or damage suffered by the Client, its agents, servants or representative howsoever arising or whether connected with the Services provided by SETSCO herein.

## **BP-266**

### **Tests on Thermal Insulation Paint 'Insultec'**

#### **EXECUTIVE SUMMARY**

The laboratory phase of the study on 'Insultec' paint revealed the following properties: -

- Thermal conductivity value (K-value) of 0.0625 W/mk (ASTM E1530-04)
- Average reflectivity of
  - 10.2 % (Ultraviolet)
  - 79.8 % (Visible)
  - 83.8 % (Near-infrared)
- Near Room Temperature emissivity of 0.87 to 0.89 (ASTM C1371-04)

Controlled experiments on the roofs of a building in Singapore indicated a surface temperature of about 10 °C and 11 °C lower, respectively externally and internally, between a surface that had been coated with 'Insultec' compared to a similar surface which was left uncoated.

Energy simulations indicated a potential 39% energy savings in the topmost unit of a 15-storey apartment block if the roof is coated with 'Insultec'.

#### 4.0 CONCLUSION

- 4.1 A study was commissioned to measure the conductivity, reflectivity and emissivity of 'Insultec' paint coated samples, as well as potential energy savings, using a computer simulation, from the use of the paint.
- 4.2 The average conductivity values of 'Insultec' were about 0.0625 W/mK. The results thermal conductivity value is comparable to that typical of fiberglass (~0.06 W/mK).
- 4.3 Reflectivity of 'Insultec' paint over the ultraviolet, visible light and near infrared ranges was averaged respectively to about 10.2%, 79.8% and 83.8%.
- 4.4 Near room temperature emissivity ranged from 0.87 to 0.89.
- 4.5 From the controlled experiments, it was found that surface temperatures of the 'unpainted box' and 'box painted with Insultec' externally and internally differed by about 10 °C and 11 °C respectively. The surface temperatures of the 'painted box' were lower than the 'unpainted box' during the mixed weather conditions.
- 4.6 Internally within the experimental boxes, the ambient temperature within the 'painted box' was about 6 °C lower than that within the 'unpainted box'.
- 4.7 Lower internal surface temperatures result in better indoor thermal comfort. It also reduces radiant heat to surrounding buildings.
- 4.8 Energy savings (up to 39%) could potentially be achieved if the roof of the top floor unit is applied with 'Insultec' coating. This concurs with the findings of the experimental boxes, where surface temperature differences of about 10 °C between 'painted' versus 'unpainted' were registered.